



## Cyano GEL

Revision: 30/08/2017

Page 1 from 1

### Technical data

Basis	Ethyl cyano-acrylate
Consistency	Gel
Curing system	Chemical curing
Density	1,06 g/ml
Temperature resistance	-40°C tot +120°C
Open time	4 - 8 sec.
Application temperature	15 °C → 25 °C
Drying time (20°C and 60% R.H.)	1 min.

(\*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

### Product description

Cyano GEL is a non dripping gel type adhesive for the fast bonding of materials which are not exactly matching. The adhesive has a longer open time than regular cyano acrylates. The product is moisture curing.

### Properties

- High adhesive strength
- Fast cure
- Single component system without catalyst

### Applications

- Suitable for bonding metals, rubber, plastics, leather, wood, etc.

### Packaging

Colour: yellow-transparent

Packaging: tube 3 g

### Shelf life

At least 24 months in unopened packaging at a temperature as low as possible (preferably in the refrigerator).

### Substrates

Substrates: many porous and non-porous substrates

Nature: clean, dry, free of dust and grease.

Surface preparation: No pretreatment required.

We recommend a preliminary adhesion test on any substrate.

### Application method

Application method: Apply the adhesive evenly on one of the parts to be glued on. Apply sufficient adhesive to obtain a thin film after pressing. Bring the two parts together and press for at least 1 min. Good contact is essential. Maximum strength is obtained after 24 to 48 hours.

Cleaning: Uncured Cyano GEL can be removed from substrates and tools with Adhesive Remover 90A or white spirit. Cured adhesive can be removed with acetone.

Repair: With the same material

### Health- and Safety Recommendations

Take the usual labour hygiene into account. Take care not to have glue between fingers or eyelids. Cyano GEL can cause serious eye damage. Keep out of reach of children. Consult label and material safety data sheet for more information.

### Remarks

- After using, clean nozzle and tube with a needle and close the cap.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.